

IN THE CLAIMS:

This listing is a listing of claims as they currently stand.

1. (Previously Presented) A barrier structure for copper metallization, comprising:

- a dielectric pattern formed on a surface of a substrate;
- a first Ru layer formed on the dielectric pattern;
- an oxide film formed by oxidizing an upper part of the first Ru layer;
- a second Ru layer formed in contact with the oxide film; and
- a Cu layer formed on the second Ru layer.

2. (Previously Presented) The barrier structure of claim 1, wherein the substrate is a silicon substrate.

3. (Previously Presented) The barrier structure of claim 1, wherein the first Ru layer and the second Ru layer are formed by using a sputtering or CVD (chemical vapor deposition) and the first Ru layer has a thickness in a range from about 80 angstroms to about 120 angstroms.

4. (Previously Presented) The barrier structure of claim 1, wherein the oxide film is made of Ru<sub>x</sub>O<sub>y</sub> formed by a plasma treatment using N<sub>2</sub>O or O<sub>2</sub>.

5. (Previously Presented) The barrier structure of claim 4, wherein the thickness of the oxide film is about 250 angstroms, which is obtained by oxidizing an upper part of the first Ru layer.

6. (Previously Presented) The barrier structure of claim 4, wherein the ratio of x:y = 1:2.

7. (Withdrawn) A method for fabricating a barrier structure for copper metallization, comprising the steps of:

- forming a dielectric pattern on a surface of a substrate;
- forming a first Ru layer on the dielectric pattern;

forming an oxide film in a surface region of the first Ru layer;  
forming a second Ru layer in contact with the oxide film; and  
forming a Cu layer on the second Ru layer.

8. (Withdrawn) The method of claim 7, wherein the substrate is a silicon substrate.

9. (Withdrawn) The method of claim 7, wherein the first Ru layer and the second Ru layer are formed by using a sputtering or CVD(chemical vapor deposition) and has a thickness in a range from about 80 angstroms to about 120 angstroms.

10. (Withdrawn) The method of claim 7, wherein the oxide film is made of  $Ru_xO_y$  formed by a plasma treatment using  $N_2O$  or  $O_2$ .

11. (Withdrawn) The method of claim 10, wherein the thickness of the oxide film is about 250 angstroms, which is obtained by oxidizing an upper part of the first Ru layer.

12. (Withdrawn) The method of claim 10, wherein the ratio of  $x:y = 1:2$ .

13. (Previously Presented) The barrier structure of claim 1, wherein the first Ru layer, the oxide film and the second Ru layer collectively form a conductive barrier structure for the Cu layer.

14. (Withdrawn) The barrier structure of claim 7, wherein the first Ru layer, the oxide film and the second Ru layer collectively form a conductive barrier structure for the Cu layer.